


Runtecure DETX

Properties and Characteristics



Specifications

Property	Value
CAS Number	82799-44-8
Other Names	2,4-diethyl thioxanthone
Appearance	Yellow or off-yellow powder
Assay	98% min
Melting point	70-75°C
Ash	0.1% max
Loss on drying	0.25% max

Applications

Used as a photo initiator in UV-curing resins, inks, coatings, adhesives; for wood, metal, and plastic.

Packaging

20kg fiber drum.